

Technical data sheet for Bible Paper Sunset g.28 sqm.

Property	Unit	Target	Tolerance		Standard
Basis Weight	g/sqm.	28	26,5	29.5	UNE-EN ISO 536:1997
Thickness	My	32	30,5	33,5	UNE-EN ISO 534:2005
Bulk	Cubic cm/g	1,143			UNE-EN ISO 534:2005
Air permeability	Cubic cm/min.	70	30	110	UNE 57066-4:1987 ISO 5636-2:1984
Tensile strength	g/15mm	2600	2300		ISO 1924-2:2008
Wire side smoothness	MI/min	60	30	90	UNE 57080-2:1988 ISO 8791-2:1190
Felt side smoothness	MI/min	90	60	120	UNE 57080-2:1988 ISO 8791-2:1190
Brightness	%ISO	90	88	92	ISO 2470:1999
Fluorescence	%ISO	11	0	0	ISO 2470:1999
Opacity	%ISO	80	78,5	0	UNE 57063:2003 ISO 2471:2008
Contact angle	0	90	80	100	TAPPI T 458
Moisture Content	%	4,5	3,5	5,5	UNE 20287:1996 ISO 287:1985
Pure Cellulose	%	100	100	100	UNE-EN ISO 536:1997

Laboratory conditions:

Temperature 23 Celsius +/- 2

Relative Humidity 50% +/-5